University of California

Ernest O. Lawrence Radiation Laboratory

TWO-WEEK LOAN COPY

This is a Library Circulating Copy which may be borrowed for two weeks. For a personal retention copy, call Tech. Info. Division, Ext. 5545

Berkeley, California

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

UCRL-10111

UNIVERSITY OF CALIFORNIA

Lawrence Radiation Laboratory
Berkeley, California

Contract No. W-7405-eng-48

DIFFUSION OF PHOSPHORUS IN SILICON FROM THE AZEOTROPE OF PHOSPHORUS PENTOXIDE AND WATER

Robert P. Lothrop

March 6, 1962

DIFFUSION OF PHOSPHORUS IN SILICON FROM THE AZEOTROPE OF PHOSPHORUS PENTOXIDE AND WATER

Robert P. Lothrop

Lawrence Radiation Laboratory
University of California
Berkeley, California

March 6, 1962

I. Introduction

Present methods for predepositing phosphorus in silicon lack sufficient control and reproduciability to meet the exacting requirements of large-area silicon radiation detectors. Unlike transistor fabrication techniques--in which diffusion at high temperatures and long times are common--radiation detectors, for certain applications, require shallow diffusions and therefore low diffusion temperatures: temperatures in the range of 600 to 900°C, and junction depths of the order of 300 to 5000 Å.

The source commonly used for the predeposition of phosphorus is phosphorus pentoxide. In order to improve the control over that obtainable with phosphorus pentoxide, the following phosphorus compounds were screened: PCl_3, PF_5, $POCl_3$, PH_3, and the azeotrope of P_2O_5 and H_2O. The method used in the last case and the results obtained proved to be of interest and are reported here.

II. Source Preparation

The azeotrope of phosphorus pentoxide and water has the following properties:[1]

---

1. J.R. Van Wazer, Phosphorus and its Compounds, (Interscience Publishers, Inc., New York, 1958), Vol. 1, p. 773.

(a) Composition: 92.4% P_2O_5, 7.6% H_2O;

(b) Boiling point: 864°C;

(c) Vapor pressure: $\log P_{mm} = 8.7788 - \frac{5.9080 \times 864}{T}$,

where P is the pressure in mm of Hg, and

T is the temperature in °K.

The azeotrope is readily prepared by heating metaphosphoric acid in a platinum boat at 800°C for several hours. Since the source is an azeotropic mixture, its composition is conveniently maintained by its frequent use.

III. Method of Obtaining Predeposit

The prepared source in a platinum boat was used in the furnace, and located upstream from the wafers. Nitrogen gas flowing at the rate of 1/2 liter per minute from boiling liquid nitrogen was used as the carrier in a 2-in.-diameter quartz tube. To minimize phosphorus contamination near the furnace area the exhaust gases were led to a fume hood.

Satisfactory predeposits have been obtained by subjecting suitably cleaned wafers to the vapors for periods of 60 min to 16 hr, and at temperatures in the range of 600 to 800°C. Temperatures and times different from the indicated ones may also be used.

IV. Results

1. Predeposit at 800°C for 60 min

Wafers of approximately 1500 ohm-cm, p-type silicon gave the following surface sheet resistances:[2]

---

2. Sheet resistances were measured with a four-point probe with equally spaced points.

Wafer #	ohms/□	Wafer #	ohms/□
627	68	541	77
628	75	542	64
629	104	545	64

2. Predeposit at 600°C for 16 hr

Wafers of approximately 1500 ohm-cm, p-type silicon gave the following sheet resistances:

Wafer #	ohms/□	Wafer #	ohms/□
537	4.5×10^3	538	4.5×10^3
539	4.5×10^3		

3. Predeposit at 800°C for 60 min followed by diffusion at 900°C for 30 min

Wafers of approximately 1500 ohm-cm, p-type silicon gave the following sheet resistances:

Wafer #	ohms/□	Wafer #	ohms/□
658	25	518	32
659	25	519	31
517	32	520	30

V. Discussion

Silicon wafers predeposited at 800°C for 60 min do not have the heavy phosphosilicate glass layer commonly obtained by the use of P_2O_5 or other sources. However, a hydrophilic thin layer is present and may be removed by washing with 25% HF. The layer is sufficiently thin that contact to the silicon may be made by pressure points. Uniform large-area predeposits were obtained in all cases. Wafers diffused by this procedure also made radiation detectors with desirable characteristics.

The observed variation in surface sheet resistances were probably due

to a nonuniform furnace temperature profile.

VI. Conclusion

The azeotrope of phosphorus pentoxide and water provides a unique source of phosphorus whose composition is invariant and whose vapor pressure is controlled by furnace temperature. Its use gives reproducible results particularly valuable at the low temperatures required for the shallow diffusion of silicon radiation detectors.

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.