UG25
LBL-17293
Summary
c1

Lawrence Berkeley Laboratory
UNIVERSITY OF CALIFORNIA

Materials & Molecular Research Division

To be presented at the Third International Conference of Infrared Physics (CIRP 3), Zurich, Switzerland, July 23-27, 1984

FAR INFRARED OPTICAL PROPERTIES OF $NbSe_3$

W.A. Challener and P.L. Richards

RECEIVED
LAWRENCE
BERKELEY LABORATORY
APR 17 1984
LIBRARY AND
DOCUMENTS SECTION

February 1984

For Reference
Not to be taken from this room

Prepared for the U.S. Department of Energy under Contract DE-AC03-76SF00098

LBL-17293 Summary c.1

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. While this document is believed to contain correct information, neither the United States Government nor any agency thereof, nor the Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or the Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or the Regents of the University of California.

LBL-17293
(Summary)

W.A. Challener and P.L. Richards

FAR INFRARED OPTICAL PROPERTIES OF $NbSe_3$

Department of Physics, University of California,
and Materials and Molecular Research Division,
Lawrence Berkeley Laboratory
Berkeley, California 94720, U.S.A.

$NbSe_3$ is a prototype for sliding charge density wave (CDW) systems. It undergoes independent and incommensurate CDW phase transitions at T_1 = 145 K, and T_2 = 59 K. At each transition a fraction of the free carriers present at room temperature condense into a CDW. The oscillator strength of the condensed carriers can appear in a low frequency pinned mode [1], a single-particle continuum above a CDW energy gap [2], and coupled CDW carrier-optical phonon modes (phase phonons) [3].

We have measured the far infrared reflectance of $NbSe_3$ and have used a Kramers-Kronig analysis to obtain the estimate of the frequency dependence of the conductivity, $\sigma_1(\omega)$ shown in Fig. 1(a). The qualitative features of the conductivity include many phonons which appear below T_2, and a low frequency contribution from the free carriers and the pinned mode.

General arguments show that at 2 K a charge density (CDW) energy gap exists between 120 and 190 cm^{-1}, the relaxation time(s) of the free carriers and CDW pinned mode is $>3\times10^{-12}$ s, and the ratio of the free carrier concentration to band mass is $<2\times10^{20}$ cm^{-3}/m_0.

A detailed model fit to the conductivity shown in Fig. 1(b) reproduces the data very accurately. It gives estimates of carrier concentrations and relaxation times, electron-phonon coupling constants and the size of the CDW energy gap. When analyzing a limited data set from a very complicated physical system like $NbSe_3$, however, one cannot be entirely certain that all of the relevant physics is included in the model. As our knowledge about $NbSe_3$ increases, the fitting procedures used here may have to be modified. It seems clear, however, that the far infrared reflectance data will provide strong constraints to any proposed model.

We particularly wish to thank P. Monceau, who provided the $NbSe_3$ used for these measurements, and L.M. Falicov, P.A. Lee, N.P. Ong, A.M. Portis, and T. Rasing for useful discussions. This work was supported by the Director, Office of Energy Research, Office of Basic Energy Sciences, Materials Sciences Division of the U.S. Department of Energy under Contract No. DE-AC03-76SF00098.



Figure 1. (a) Kramers-Kronig calculation of $\sigma_1(\omega)$ from the measured reflectance. (b) Model calculation of $\sigma_1(\omega)$ fitted to data.

References

1. J. Bardeen, Proceedings of the International School of Physics "Enrico Fermi" Varenna, Italy, July 4-6, 1983 (to be published); G. Gruner, A. Zettl, W.G. Clark, J. Bardeen, Phys. Rev. B24, 7247 (1981).

2. P.A. Lee, T.M. Rice, P.W. Anderson, Sol. St. Comm. 14, 703 (1974).

3. M.J. Rice, Phys. Rev. Lett. 37#1, 36 (1976).

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.

TECHNICAL INFORMATION DEPARTMENT
LAWRENCE BERKELEY LABORATORY
UNIVERSITY OF CALIFORNIA
BERKELEY, CALIFORNIA 94720